



METHOD OF MANUFACTURING CONTINUOUS FOAM FROM THERMOPLASTIC ELASTOMERIC MATERIAL IN ATMOSPHERE

FIELD OF THE INVENTION

5 The present invention relates to a method of manufacturing foamed
sheet from plastics and more particularly to a method of manufacturing
continuous foamed sheet having properties of both typical rubber foam and
plastic foam materials from a thermoplastic elastomeric material under one
atmospheric pressure by taking advantage of the well known method of
10 manufacturing continuous foam from rubber.

BACKGROUND OF THE INVENTION

Conventionally, foam materials are classified as a rubber based foam
material and a plastic based foam material depending on the raw material.
15 Also, applications of rubber based foam material are different from that of
plastic based foam material due to different properties thereof. For example,
typically ethylene vinyl acetate (EVA) or a mixture of EVA and polyethylene
(PE) is used as the raw material in the foaming process of manufacturing a
plastic foam material. As such, the manufactured plastic foam material has
20 advantages of being subject to cold-molding or hot-molding to form products
having complicated shape, simple foaming recipe , and easy coloring. The
foaming process and applications of products made therefrom are well
known. For example, many consumer goods such as shoes, mats, or the like
are made from a plastic foam material. Disadvantages thereof, however, are
25 poor elasticity and poor slip resistance.

Moreover, typically a rubber material such as a mixture of polyvinyl
chloride (PVC) and acrylonitrile butadiene rubber (NBR) is used as the raw

material in the process of manufacturing a rubber foam material in atmosphere. The manufactured rubber foam material is without the disadvantages associated with the plastic foam material. Further, it has improved weather-proof and physical properties. As such, it is often used as material in manufacturing buoyant devices, pads, or the like. However, the recipe of the rubber foam compound are relatively complex. Also, dust is susceptible to generation in the manufacturing process, resulting in an environmental pollution. In addition, it has disadvantages of being difficult of post-molding to form products having complicated shape, and being difficult of recycling the waste material. Gradually, they are banned in use due to environmental pollution caused by PVC.

Thus, it is desirable to provide a method of manufacturing continuous foam having properties of both typical rubber foam and plastic foam materials from a thermoplastic elastomeric material by using the well known manufacturing process in order to improve the properties of foam material and increase applications thereof.

SUMMARY OF THE INVENTION

A primary object of the present invention is to provide a method of manufacturing continuous foamed sheets from a thermoplastic elastomeric material under one atmospheric pressure. The method comprises using thermoplastic elastomer as a substrate of the thermoplastic elastomeric composite, adding composing agent, foaming agent, and crosslinking agent and other additives into the substrate of the thermoplastic elastomeric composite, kneading and rolling the thermoplastic elastomeric composite for forming a continuous sheet by means of a conventional rubber continuous foaming device, conveying the continuous sheet to an oven and enabling the

continuous sheet to be baked in the oven and to foam under one atmospheric pressure and cooling the continuous foamed sheet to produce the foam material of the present invention. By utilizing the present invention, the above drawbacks of the prior art can be overcome.

5 One object of the present invention is to use a conventional continuous foaming process by taking advantage of conventional continuous foaming techniques and devices in which the method comprises the steps of kneading and rolling are performed on the thermoplastic elastomeric composite for forming a continuous foamed sheet, conveying the sheet to an oven, baking
10 the continuous sheet under one atm, rolling the foamed sheet, and producing the continuous foam material in rolls. In such a manner, it is possible of manufacturing a continuous foam material in rolls as a replacement of the current PVC/NBR mixture or any of other rubber foam materials formed of rubber.

15 Another object of the present invention is to, after kneading and rolling the thermoplastic elastomeric composite cut the continuous sheet into a plurality of sheet members with a predetermined size, stack predetermined number of sheets in a heat mold for hot mold pressing and obtaining a molded block, and convey the block to an oven to bake in the oven a foam
20 under one atm. As such, it is possible of manufacturing a foam material having a predetermined shape from the thermoplastic elastomeric material under oneatmospheric pressurewithout having to greatly modifying the prior manufacturing processes.

25 Still another object of the present invention is to provide a continuous foam having advantages of good elasticity and being slip resistant as a typical rubber foam material, and simple recipe, easy coloring, easy post-processing, and recycling as a typical plastic foam material.

The above and other objects, features and advantages of the present invention will become apparent from the following detailed description taken with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

5 FIG. 1 is a flow chart illustrating a process according to a first preferred embodiment of the invention; and

 FIG. 2 is a flow chart illustrating a process according to a second preferred embodiment of the invention.

10 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

 The invention is directed to a method of manufacturing continuous foamed sheets from a thermoplastic elastomeric composite under one atm. The method comprises the steps of using thermoplastic elastomer as a substrate for the thermoplastic elastomeric composite, adding additive
15 agents, foaming agent, and crosslinking agent into the substrate to form the thermoplastic elastomeric composite, kneading and rolling above materials for forming a continuous sheet by means of a conventional rubber continuous foaming process, then conveying the continuous sheet to an oven, enabling the continuous sheet to be baked in the oven and to foam under
20 oneatmospheric pressureand cooling the foamed sheet to produce the foam material of the invention. The foam material not only has advantages of good elasticity and being slip resistant as a typical rubber foam material but also has advantages of simple recipe, easy coloring, easy post-processing, and recycling as a typical plastic foam material.

25 In the invention the foamed sheet is a styrenic thermoplastic elastomer such as styrene butadiene styrene (SBS), styrene-ethylene/butene-styrene (SEBS), or styrene isoprene styrene (SIS). In the thermoplastic elastomeric composite there are also added other rubber materials, thermoplastic

elastomeric materials, or plastic materials in a predetermined weight percentage. Finally, add foaming agent, crosslinking agent, and composing agent in a predetermined weight percentage into the thermoplastic elastomeric composite to produce the thermoplastic elastomer composite of the invention.

In the process according to a first preferred embodiment of the invention prior kneader, roll mill, and foaming device are used the same as that employed in a conventional one-stage based rubber continuous foaming process illustrated in a flow chart of FIG. 1. Kneading, rolling, and foaming steps are performed sequentially on the thermoplastic elastomeric composite to be processed and in which in step 101 the invention first pour components of the thermoplastic elastomeric composite in a predetermined weight percentage into a kneader, roll mill, and two-roll mill (or Banbury mixer) for uniformly mixing in a temperature ranged from 90°C to 130°C; in step 102 convey the uniformly mixed thermoplastic elastomeric composite to a three-roll mill for rolling to form a continuous sheet with required width and thickness; in step 103 convey the continuous sheet to an oven to bake in a temperature ranged from 150°C to 180°C about oneatmospheric pressurefor foaming the continuous sheet wherein the baking time of the continuous sheet is about 10 to 30 minutes depending on the size and the thickness of the sheet, and the foamed continuous sheet is then conveyed from the oven; and in step 104 finally cool the foamed continuous sheet and roll the same to produce the rolled, continuous foam material.

In the process according to a second preferred embodiment of the invention prior kneader, roll mill, and foaming device are used the same as that employed in a conventional two-stage based rubber continuous foaming process illustrated in a flow chart of FIG. 2. Kneading, rolling, and foaming steps are performed sequentially on the thermoplastic elastomeric composite

to be processed and in which in step 201 the invention first pour components of the thermoplastic elastomeric composite in a predetermined weight percentage into a kneader, roll mill, and two-roll mill (or Banbury mixer) for uniformly mixing in a temperature ranged from 90°C to 130°C; in step 202
5 convey the uniformly mixed thermoplastic elastomeric material to a two-roll mill for rolling a number of times to form a continuous sheet with required width prior to cutting into a plurality of sheet members with a predetermined size; in step 203 stack a selected weight of sheet members or a selected number of sheet members having a required weight and convey the same to
10 a mold to heat in a temperature ranged from 150°C to 180°C in a pressure about 90 to 250 kg/cm² wherein a block is formed after heating about 5 to 15 minutes depending on the size and thickness of the mold; in step 204 convey the block to an oven to bake in a temperature ranged from about 150 to 180 in a normal pressure about one atmosphere for foaming the block wherein
15 the baking time of the continuous sheet is about 10 to 30 minutes depending on the size of the block, and the foamed block is then conveyed from the oven; and in step 205 finally cool the foamed block to produce the foam material having a predetermined shape.

In the embodiments of the invention the thermoplastic elastomeric
20 material comprises the following components:

(1) Styrenic thermoplastic elastomer: The component is the substrate of the elastomeric material having a weight percentage about 50% to 100% selected from SBS, SEBS, SIS, or styrene ethylene propylene styrene (SEPS).

25 (2) Chemical foaming agent: The component having a percentage about 1% to 15% of the total weight of the polymeric raw material is selected from a chemical foaming agent (e.g., azodicarbonamide) or a physical foaming agent

(e.g., sodium bicarbonate) wherein the substrate is comprised of styrenic thermoplastic elastomer and another polymeric material which, as an additive, has an amount taken as a percentage of the total weight of the polymeric raw material.

- 5 (3) Crosslinking agent: The component having a percentage about 0.1% to 1% of the total weight of the polymeric raw material is selected from a dicumyl peroxide, 2,5-(tert-butylperoxide)-2,5-dimethylhexane or sulfur.

The inventor takes advantage of the above components to continuously manufacture a thermoplastic elastomeric foam composite in a normal
10 pressure (i.e., one atmosphere) in the above manufacturing processes. The foam material has the following advantages after being verified in experimentation:

- (1) The invention is able to manufacture a novel, PVC free foam material having properties of both typical rubber foam and plastic foam materials
15 without having to greatly modifying the prior manufacturing processes by utilizing a rubber continuous foam manufacturing technique and apparatus.

(2) The produced foam material of the invention has good elasticity and is slip resistant. Also, it is easy of coloring, has no smell of sulfuric rubber, can be recycled, and is wide in applications.

- 20 (3) The foam material of the invention has good post-processing capability. As such, it is subject to processing to form products having complicated shapes or patterns. Thus, it is particularly useful in producing products with mark, printing, and adhesive surfaces.

In addition, the invention does not limit the polymeric material as the
25 same as above in practice. Rather, one skilled in the art may add the following components into the thermoplastic elastomeric material for manufacturing foam of the invention therefrom in atmosphere depending on desired capabilities, features, or applications.

(1) Any of other polymeric materials: The component having a percentage about 0% to 50% of the total weight of the polymeric raw material is selected from a styrene butadiene rubber (SBR), polystyrene (PS), ethylene vinyl acetate (EVA), low density polyethylene (LDPE), or ethylene-propylene-diene terpolymer rubber (EPDM) so as to improve the property of foam material for fulfilling the needs.

(2) Functional additive: The component having a percentage about 0% to 50% of the total weight of the polymeric raw material is selected from an anti-static agent, a combustion retardation agent, or a reinforced agent for improving the physical properties of the foam material.

(3) Accelerator for foaming agent: The component having a percentage about 0% to 3% of the total weight of the polymeric raw material is selected from a zinc oxide or urea for improving and accelerating the foaming.

(4) Any of other additives: The component is selected from oil, hard fatty acids or hard zinc based fatty acids as processing agent, coloring agent as an additive, calcium carbonate, or wood chips for changing the property of the foam material or changing a visual effect thereof.

While the invention has been described by means of specific embodiments, numerous modifications and variations could be made thereto by those skilled in the art without departing from the scope and spirit of the invention set forth in the claims.